

Facestock		Facestock physical properties				
2 Mil White Polyester TC is a homogeneously pigmented white facestock featuring excellent tear strength, heat resistance, dimensional stability, opacity, and chemical resistance.		Imperial Value	Units	Metric Value	Units	
	Caliper: ASTM D1000	0.0020	inches	50.80	micron	
	Tensile: ASTM D882	MD	21,300	PSI	1,497	kg/cm ²
		CD	28,400	PSI	1,997	kg/cm ²

Adhesive		Adhesive physical properties				
S8025 is a high performance, clear permanent solvent acrylic pressure sensitive adhesive with balanced adhesion to a wide variety of substrates, including low surface energy plastics, engineering grade plastics, bare, coated, or painted metals, including powder coat and enamel paints. It features medium tack for good short term repositionability, low ooze, and excellent chemical and UV resistance for outdoor industrial applications.		Imperial Value	Units	Metric Value	Units	
	Type:	Solvent Acrylic				
	Caliper: ASTM D1000	0.0009	Inches	22.86	microns	
	Standard Coat Wt:			27	g/sq m	
	Minimum Appl Temp:	50	F	10	C	
	Service Temp Range:	Min	-40	F	-40	C
		Max	302	F	150	C
	Loop Tack Stainless Steel: PSTC11	50.6	oz/in	55.7	N/100 mm	

Liner		Liner physical properties				
50#SCK is a bleached, super-calendered paper stock with very good diecutting and matrix stripping properties. Suitable for back-printing with standard inks.		Imperial Value	Units	Metric Value	Units	
	Caliper: ASTM D1000	0.0032	inches	81.2800	microns	
	Basis Wt: TAPPI T410 * (24" x 36" 500 sheets)	53.9	lb/ream	86.2	g/sq m	
	Tensile: ASTM D882	MD	48.0	lb/inch	211.2	N/25 mm
		CD	26.0	lb/inch	114.4	N/25 mm
	Tear: TAPPI T414	MD	1.8	ounces	51.1	grams
		CD	2.0	ounces	56.8	grams

Liner Release:		Total Construction Caliper
TMLI 90° removal of Liner from Facestock.		(approximate):
Rate of Removal	Grams/2" Width	
400 inches/min.	55	0.0061 inches (6.1 mils; 154.9 microns)

Features and Benefits

- Opaque white facestock with very good hiding power and physical strength
- Glossy clear topcoat which accepts most flexographic, letterpress, and rotary screen inks
- Excellent thermal transfer printability with most wax/resin and resin ribbons
- Topcoat and adhesive have excellent chemical resistance

Applications and Uses

This product is suitable for wide variety of durable labeling applications such as:

- Product identification labels
- Barcodes and rating plates
- Work in progress labels (WIP)
- Property identification and asset tags
- Durable goods labeling
- UL and UL-c recognized for indoor and outdoor use. Specific recognition information will be found in UL file # MH17205.

Printing and Converting

The topcoat is designed for printing by flexography with most solvent and some water based inks. Specially formulated inks are normally not needed, however, testing is recommend prior to final ink selection. Suitable for thermal transfer printing applications with select ribbons and printer models. This product can be diecut and stripped at high speeds on standard web-fed presses. Sample labels in a variety of shapes have been successfully dispensed and applied with standard labeling systems.

RoHS/Regulation 2002/95/EU

The substances listed in article 4 lid 1 of 2002/95/EU (RoHS) are not intentionally used in this product. The concentration limits of these substances will not exceed the set maximum concentration limits as provided in the proposed amendment for 2002/95/EU.

Shelf Life

Unless specified otherwise in this document, one year when stored at 72°F at 50% RH

Note:

The technical data presented is from tests we believe to be reliable but should be considered representative or typical only and should not be used for specifications purposes. This product should be tested thoroughly under end-use conditions to ensure it meets the requirements of the specific application.

Appendix

Performance Data:

The following technical data should be considered representative or typical only and should not be used for specification purposes.

Surface	Initial (15 minute dwell)		72 Hours at Room Temperature		72 Hours at 120°F		9
	oz/in	N/100mm	oz/in	N/100mm	oz/in	N/100mm	
1. Stainless Steel	62.7	69	65.8	72.4	75.2	82.7	8
2. Aluminum	42.7	47	52.8	58.1	67.2	73.9	8
3. Polypropylene	52.3	57.5	62.9	69.2	59.2	65.1	5
4. HDPE	32	35.2	32	35.2	36.8	40.5	3
5. LDPE	24.8	27.3	42.1	46.3	35.4	38.9	2
6. ABS Plastic	56.2	61.8	65.6	72.2	56	61.6	5

Environmental Performance: Chemical Resistance test results

The performance results are based on 4 hour immersions at room temperature unless otherwise noted (gasoline is 1 hour). Samples were applied to stainless steel panels and conditioned for 24 hours before immersion and evaluated immediately upon removal. Adhesion measured at 180° peel.

Chemical	Adhesion to Stainless Steel		Visual Appearance	
	oz/in	N/100mm		
1. 70% IPA	43	47.3	No Change	
2. Tide® Detergent	57.9	63.7	No Change	
3. Engine Oil (10W30)	53.6	59	No Change	
4. Water	60	66	No Change	
5. Ammonia - pH 11	42.4	46.6	Edge Swell	
6. 409® Cleaner	56.2	61.8	No Change	
7. Toluene	29.4	32.3	Edge Swell	
8. Brake Fluid	51	56.1	No Change	
9. Reference Fuel C	48.8	53.7	Edge Swell	
10. Kerosene K1	56.5	62.2	No Change	
11. Heptane	43	47.3	No Change	

Compliance Recognition: UL CSA C-U



Underwriters Laboratories, Inc.

[Add Record](#) [Change Record](#) [Delete Record](#)

Substrates	Minimum Temperature		Maximum Temperature		(I=Indoor C I/O=Indoor & C
	°F	°C	°F	°C	
1. Acrylic Paint	-40	-40	302	150	I/O
2. Alkyd Enamel	-40	-40	302	150	I/O
3. Aluminum	-40	-40	302	150	I/O
4. Epoxy Paint	-40	-40	302	150	I/O
5. Galvanized Steel	-40	-40	302	150	I/O
6. Polyester Paint	-40	-40	302	150	I/O
7. Polyester PCP*	-40	-40	302	150	I/O
8. Polyurethane PCP*	-40	-40	302	150	I/O
9. Porcelain	-40	-40	302	150	I/O
10. Stainless Steel	-40	-40	302	150	I/O
11. Epoxy PCP*	-40	-40	302	150	I/O
12. Melamine	-40	-40	212	100	I/O
13. Nylon	-40	-40	212	100	I/O
14. Polycarbonate	-40	-40	212	100	I/O
15. Thermoset Polyester	-40	-40	212	100	I/O
16. ABS Plastic	-40	-40	176	80	I/O
17. PBT Plastic	-40	-40	176	80	I/O
18. Polystyrene	-40	-40	176	80	I/O
19. Polyphenylene Oxide	-40	-40	176	80	I/O
20. Polypropylene	-40	-40	176	80	I/O
21. and others					
22. *PCP=Powder Coat Paint					

Recognized Ribbons:

Armor "AXR7+", Armor "AXR8", Armor "AXR600", Astro Med Inc "R-5", Astro Med "RF", Astro Med "RY", Coding Prds "5940", Dai Nippon "R-300", Dai Nippon "R-510", limak "SP-410", limak "SP-330", limak "Primemark", Intermec "TMX 1500", Intermec "TMX 3200", ITW "B324", Kurz "K300", Kurz "K500", Kurz "K501", NCR "Promark 3", NCR "Pacesetter", NCR "Ultra V", NCR "Perma Max", NCR "K3", Ricoh "B110C", Ricoh "B110CR", Ricoh "120EC", Sato Corp. "Premier 1", Sony "TR4070", Sony "TR4075", Sony "TR5070", Sony "TR6070", Sony "TR6075", Sony "TRX75", Sony "Signature Series Resin", Union Chemicar "US300", Zebra "5095", Zebra "5100", Zebra "5175", Zebra "5463", Zebra "5555", Zebra "Z-4100" and others.



Tested by Underwriters Laboratories, Inc.
to meet the requirements of the Canadian Standards Association for labeling materials

[Add Record](#) [Change Record](#) [Delete Record](#)

Substrates	Minimum Temperature		Maximum Temperature		(I=Indoor Only I & Outdoor)
	°F	°C	°F	°C	
1. Metals	-40	-40	302	150	I/O
2. Electrostatic Paints	-40	-40	302	150	I/O
3. Plastics Group I	-40	-40	212	100	I/O
4. Plastics Group II	-40	-40	176	80	I/O
5. Plastics Group III	-40	-40	176	80	I/O
6. Plastics Group IV	-40	-40	176	80	I/O
7. Plastics Group V	-40	-40	176	80	I/O
8. Plastics Group VI	-40	-40	176	80	I/O
9. Plastics Group VII	-40	-40	176	80	I/O
10. Plastics Group VIII	-40	-40	176	80	I/O

Recognized Ribbons: Armor "AXR7+", Armor "AXR8", Armor "AXR600", Astro Med "RY", Dai Nippon "R-300", Dai Nippon "R-510", Kurz "K500", NCR "Promark 3", Ricoh "B110C", Ricoh "B110CR", Sato Corp. "Premier 1", Sony "TR4070", Sony "TR5070", Sony "TRX75", Sony "Signature Series Resin", Union Chemcar "US300", Zebra "5100", and others.

409® is a registered trademark of the Clorox Company
Tide® is a registered trademark of the Procter & Gamble Company

The information on compliance conditions, substrates, and printing products contained in the tables above represent a summary of recognized or acceptable conditions and printing products. Other conditions, substrates, and printing products may be recognized with this material. Please consult the specific compliance organization records or specific files for a complete listing.

Warranty

All statements, technical information and recommendations about AVERY DENNISON products are based upon tests believed to be reliable but do not constitute a guarantee or warranty. All AVERY DENNISON products are sold with the understanding that PURCHASER has independently determined suitability of such products for its purposes. AVERY DENNISON products are warranted to the original purchaser to be free from defects in material or workmanship for a period of one year from date of shipment. Purchaser's sole and exclusive remedy for breach of this warranty shall be the replacement of the defective products or, at AVERY DENNISON's option, the issuance of a credit or refund in an amount up to the purchase price of the defective product. In no event shall AVERY DENNISON be responsible for claims beyond the purchase price of the defective product.

THE WARRANTY SPECIFICALLY SET FORTH ABOVE IS IN LIEU OF ANY OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTIES OR MERCHANTABILITY, FITNESS FOR ANY PARTICULAR USE AND/OR NON-INFRINGEMENT. AVERY DENNISON SPECIFICALLY DISCLAIMS AND EXCLUDES ALL OTHER SUCH WARRANTIES. IN NO EVENT SHALL AVERY DENNISON BE LIABLE TO PURCHASER OR ANY OTHER PARTY FOR INDIRECT, CONSEQUENTIAL, INCIDENTAL, SPECIAL OR PUNITIVE DAMAGES.

No representative or agent of AVERY DENNISON is authorized to give any guarantee or warranty or make any representation contrary to the above. No waiver, alteration, addition or modification of the foregoing conditions shall be valid unless made in writing and signed by an executive officer of AVERY DENNISON.

www.na.fasson.com



Avery Dennison
Fasson Roll North America
8080 Norton Parkway
Mentor, OH 44060
800-944-8511 (US & Canada)
52-55-5093-0100 (Mexico)

