

**Fasson® 2 Mil Matte Silver Checkerboard Polyester
TC/S8015/50#SCK**

**Product Data Sheet
Spec#: 78199**

Facestock		Facestock physical properties				
A 2 mil matte silver voidable polyester film incorporating a pattern release layer which yields a 3 mm checkerboard pattern for tamper evidence when removed from a substrate. The facestock is top coated to enhance flexographic, UV letterpress, and thermal transfer printing.		Imperial Value	Units	Metric Value	Units	
	Caliper: ASTM D1000	0.0020	inches	50.80	microns	
	Tensile: ASTM D882	MD	28,000	PSI	1,968	Kg/sq.cm
		CD	34,000	PSI	2,390	Kg/sq.cm

Adhesive		Adhesive physical properties				
S8015 adhesive is a high strength clear adhesive featuring high initial tack, adhesion and shear. Offers strong permanent bonding to a wide variety of substrates including high surface energy (HSE), low surface energy (LSE) and powder coat substrates. Excellent chemical and UV resistance.		Imperial Value	Units	Metric Value	Units	
	Type:	Solvent Acrylic				
	Caliper: ASTM D1000	0.0010	inches	25.40	micron	
	Standard Coat Wt:			32	g/sq m	
	Minimum Appl Temp:	45	F	7	C	
	Service Temp Range:	Min	-30	F	-34	C
		Max	300	F	149	C
Loop Tack Stainless Steel: PSTC11	110.0	oz/in	121.0	N/100mm		

Liner		Liner physical properties				
50#SCK is a bleached, super-calendered paper stock with very good diecutting and matrix stripping properties. Suitable for back-printing with standard inks.		Imperial Value	Units	Metric Value	Units	
	Caliper: ASTM D1000	0.0032	inches	81.2800	microns	
	Basis Wt: TAPPI T410 <small>* (24" x 36" 500 sheets)</small>	53.9	lb/ream	86.2	g/sq m	
	Tensile: ASTM D882	MD	48.0	lb/inch	211.2	N/25 mm
		CD	26.0	lb/inch	114.4	N/25 mm
	Tear: TAPPI T414	MD	1.8	ounces	51.1	grams
CD		2.0	ounces	56.8	grams	

Liner Release:		Total Construction Caliper
TMLI 90° removal of Liner from Facestock.		(approximate):
Rate of Removal	Grams/2" Width	
400 inches/min.	60	0.0062 inches (6.2 mils; 157.48 microns)

Features and Benefits

- Opaque facestock with good hiding power and physical strength
- Top coated to accept most flexographic, letterpress, and rotary screen inks
- Good thermal transfer printability with most wax/resin and resin ribbons
- Good adhesion to most substrates
- Tamper-evident when removal from substrate is attempted
- 3 mm checkerboard pattern left on facestock and substrate when removed

Applications and Uses

This product is suitable for wide variety of labeling applications such as:

- Product authentication labels
- Nameplates and rating plates
- Property identification and asset tags
- Security labels for over the counter drugs and other packaging applications
- Non-transferable labels or security tags

See Technical Bulletin "Tamper-Evident Polyesters" for proper end use and surface preparation

Printing and Converting

The top coat is designed for printing by flexography with most solvent and some water based inks. Specially formulated inks are normally not needed, however, testing is recommended prior to final ink selection. Suitable for thermal transfer printing applications with select ribbons and printer models. This product can be die cut and stripped at moderate speeds on standard web-fed presses. Not intended for auto-application. Dispensing tests must be conducted prior to committing to production..

RoHS/Regulation 2002/95/EU

The substances listed in article 4 lid 1 of 2002/95/EU (RoHS) are not intentionally used in this product. The concentration limits of these substances will not exceed the set maximum concentration limits as provided in the proposed amendment for 2002/95/EU.

Shelf Life

Unless specified otherwise in this document, one year when stored at 72°F at 50% RH

Note:

The technical data presented is from tests we believe to be reliable but should be considered representative or typical only and should not be used for specifications purposes. This product should be tested thoroughly under end-use conditions to ensure it meets the requirements of the specific application.

Appendix

Performance Data:

The following technical data should be considered representative or typical only and should not be used for specification purposes.

Surface	Initial (15 minute dwell)		72 Hours at Room Temperature		72 Hours at 120°F		9
	oz/in	N/100mm	oz/in	N/100mm	oz/in	N/100mm	
1. Stainless Steel	82.1	90.3	73.7	81.1	77.4	85.1	8
2. Aluminum	83.7	92.1	54.8	60.3	60.5	66.6	8
3. Polypropylene	52.2	57.4	23.9	26.3	65.4	71.9	5
4. HDPE	43.2	47.5	40.4	44.4	41.7	45.9	4
5. LDPE	42.1	46.3	74.5	82	21.4	23.5	
6. ABS Plastic	73	80.3	82.4	90.6	78.5	86.4	2

Environmental Performance: Chemical Resistance test results

The performance results are based on 4 hour immersions at room temperature unless otherwise noted (gasoline is 1 hour). Samples were applied to stainless steel panels and conditioned for 24 hours before immersion and evaluated immediately upon removal. Adhesion measured at 180° peel.

Chemical	Adhesion to Stainless Steel		Visual Appearance
	oz/in	N/100mm	
1. 70% IPA	73.4	80.7	No Change
2. Tide® Detergent	58.5	64.4	No Change
3. Engine Oil (10W30)	62.5	68.8	No Change
4. Water	66.7	73.4	No Change
5. Ammonia - pH 11	27.3	30	No Change
6. 409® Cleaner	28.9	31.8	No Change
7. Toluene	17.8	19.6	No Change
8. Brake Fluid	68.3	75.1	No Change
9. Reference Fuel C	35.2	38.7	No Change

10. Kerosene K1	46.2	50.8	No Change
11. Heptane	12.9	14.2	No Change

Compliance Recognition: UL CSA C-U

409® is a registered trademark of the Clorox Company
Tide® is a registered trademark of the Procter & Gamble Company

The information on compliance conditions, substrates, and printing products contained in the tables above represent a summary of recognized or acceptable conditions and printing products. Other conditions, substrates, and printing products may be recognized with this material. Please consult the specific compliance organization records or specific files for a complete listing.

Warranty

All statements, technical information and recommendations about AVERY DENNISON products are based upon tests believed to be reliable but do not constitute a guarantee or warranty. All AVERY DENNISON products are sold with the understanding that PURCHASER has independently determined suitability of such products for its purposes. AVERY DENNISON products are warranted to the original purchaser to be free from defects in material or workmanship for a period of one year from date of shipment. Purchaser's sole and exclusive remedy for breach of this warranty shall be the replacement of the defective products or, at AVERY DENNISON's option, the issuance of a credit or refund in an amount up to the purchase price of the defective product. In no event shall AVERY DENNISON be responsible for claims beyond the purchase price of the defective product.

THE WARRANTY SPECIFICALLY SET FORTH ABOVE IS IN LIEU OF ANY OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTIES OR MERCHANTABILITY, FITNESS FOR ANY PARTICULAR USE AND/OR NON-INFRINGEMENT. AVERY DENNISON SPECIFICALLY DISCLAIMS AND EXCLUDES ALL OTHER SUCH WARRANTIES. IN NO EVENT SHALL AVERY DENNISON BE LIABLE TO PURCHASER OR ANY OTHER PARTY FOR INDIRECT, CONSEQUENTIAL, INCIDENTAL, SPECIAL OR PUNITIVE DAMAGES.

No representative or agent of AVERY DENNISON is authorized to give any guarantee or warranty or make any representation contrary to the above. No waiver, alteration, addition or modification of the foregoing conditions shall be valid unless made in writing and signed by an executive officer of AVERY DENNISON.

www.na.fasson.com



Avery Dennison
Fasson Roll North America
8080 Norton Parkway
Mentor, OH 44060
800-944-8511 (US & Canada)
52-55-5093-0100 (Mexico)

